


# YAC-VOS

## Vinyltris(methylethylketoxime)silane

CAS No. 2224-33-1



Specifications:

Tests	Specification
Appearance	Colorless to light yellow transparent liquid
Assay	≥ 95.0%
MEKO	≤ 1.0%
Low boilers	≤ 2.0%
High boilers	≤ 3.0%
Density (20°C)	0.9800~1.0000g/cm <sup>3</sup>
Refractive index(nD <sup>25</sup> )	1.4525~1.4725

**Package:** 200Kg/Drum or 950Kg/IBC

**Application:**

- It is used as a crosslinking agent for room temperature vulcanized silicone rubber and silicone glass glue (neutral).

**Storage:** Keep away from open flames, hot surfaces and sources of ignition. Keep container tightly closed in a dry and well-ventilated place.



**Recommend Shelf Life:** 12 months.